



Material - DIN 2.4062

Standard Specification for Nickel and Nickel Alloy Castings

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4062 Nickel and Nickel Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.		
Silicon	Si %	0.020 max.		
Manganese	Mn %	0.050 max.	As-Cast or Annealing or Age Hardning	
Copper	Cu %	0.050 max.		
Iron	Fe %	0.200 - 0.600		
Magnesium	Mg %	0.050 max.		
Sulphur	S %	0.005 max.		
Nickel	Ni %	99.400 max.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	370 min.
-	-	-	Yield Strength in Mpa	100 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	130 min.
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
-	-	-	_		
-		-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-		-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.