



Material - DIN 2.4145

Standard Specification for Nickel-Chromium-Manganese Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4145 Nickel-Chromium-Manganese Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.		
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.200 - 2.500		
Copper	Cu %	0.500 max.	As-Cast or Annealing or Age Hardning	or Age Hardning
Iron	Fe %	2.000 max.		
Chromium	Cr %	2.000 max.		
Titanium	Ti %	0.200 - 0.400		
Nickel	Ni %	95.000 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
NiCr 2 Mn	DIN	Germany	Casting		
-	_	-	-		
-	-	-			
-	-	-	-		
-	-	·	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.