



Material - DIN 2.4605

Standard Specification for Nickel Base Alloy Plate, Sheet, Strip, Bars and Forgings

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4605 Nickel Base Alloy Plate, Sheet, Strip, Bars and Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet, Strip, Bar and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	22.000 - 24.000		
Cobalt	Co %	0.300 max.		
Aluminium	Al %	0.100 - 0.400		
Molybdenum	Mo %	15.000 - 16.500		
Iron	Fe %	1.500 max.	Mechanical Properties Tensile Strength in Mpa 650 - 900 Yield Strength in Mpa 320 min. Elongation in % 25 min. Reduction of Area in % - Hardness in BHN 240 max. Impact in Joule 180 @ RT	
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.010 max.		
Copper	Cu %	0.500 max.		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
NiCr23Mo16Al	DIN	Germany	Plate, Sheet, Strip, Bar and Forging
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.