



Material - DIN 2.4607

Standard Specification for Nickel and Nickel Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4607 Nickel and Nickel Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	22.000 - 24.000		
Cobalt	Co %	0.300 max.		
Aluminium	Al %	0.100 - 0.400		
Molybdenum	Mo %	15.000 - 16.500		
Iron	Fe %	1.500 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0015 max.		
Nickel	Ni %	Balance	Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SG-NiCr 23 Mo 16	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.