



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - DIN 2.4608

### Standard Specification for Nickel and Nickel Alloy Strips and Sheets

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4608 Nickel and Nickel Alloy Strips and Sheets

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Strip and Sheet

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 - 0.080	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.700 - 1.500		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	24.000 - 26.000		
Cobalt	Co %	2.500 - 4.000		
Molybdenum	Mo %	2.500 - 4.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.015 max.		
Tungsten	W %	2.500 - 4.000		
Nickel	Ni %	44.000 - 47.000		
Iron	Fe %	Balance	<b>Mechanical Properties</b>	
-	-	-	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	220 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**