

## Material - DIN 2.4610

## Standard Specification for Nickel and Nickel Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4610 Nickel and Nickel Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.		
Silicon	Si %	0.080 max.		
Manganese	Mn %	1.000 max.	As-Cast or Annealing or Age Hardning	
Copper	Cu %	0.500 max.		r Age Hardning
Chromium	Cr %	14.000 - 18.000		
Cobalt	Co %	2.000 max.		
Molybdenum	Mo %	14.000 - 17.000		
Phosphorus	Р%	0.025 max.		
Sulphur	S %	0.015 max.	Mechanical Properties	
Titanium	Ti %	0.700 max.	Tensile Strength in Mpa	680 - 900
Iron	Fe %	3.000 max.	Yield Strength in Mpa	275 min.
Nickel	Ni %	Balance	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	240 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
NiMo16Cr16Ti	DIN	Germany	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## **ONE STOP SOLUTION FOR METAL PARTS**