



Material - DIN 2.4633

Standard Specification for Nickel and Nickel Alloy Strip and Sheet

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4633 Nickel and Nickel Alloy Strip and Sheet

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Strip and Sheet

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.250	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	24.000 - 26.000		
Aluminium	Al %	1.800 - 2.400		
Copper	Cu %	0.100 max.		
Iron	Fe %	8.000 - 11.000		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.010 max.		
Titanium	Ti %	0.100 - 0.200		
Yttrium	Y %	0.050 - 0.120		
Zirconium	Zr %	0.010 - 0.100		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
VDM alloy 602 CA	Gravity	India	Strip and Sheet
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.