



Material - DIN 2.4636

Standard Specification for NiCrCoMoTiAl Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4636 NiCrCoMoTiAl Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 - 0.200	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.000 - 16.000		
Aluminium	Al %	4.500 - 5.500		
Copper	Cu %	0.200 max.		
Cobalt	Co %	13.000 - 17.000		
Boron	B %	0.010 - 0.025		
Iron	Fe %	1.000 max.		
Molybdenum	Mo %	3.000 - 5.000		
Phosphorus	P %	0.045 max.	Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Sulphur	S %	0.030 max.		
Titanium	Ti %	3.500 - 4.500		
Zirconium	Zr %	0.250 max.		
Nickel	Ni %	Balance		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
NiCo 15 Cr 15 MoAlTi	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.