



## Material - DIN 2.4675

### Standard Specification for NiCr23Mo16Cu Strip, Sheet, Forging and Rod

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4675 NiCr23Mo16Cu Strip, Sheet, Forging and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Strip, Sheet, Forging and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	22.000 - 24.000		
Cobalt	Co %	2.000 max.		
Aluminium	Al %	0.500 max.		
Copper	Cu %	1.300 - 1.900		
Molybdenum	Mo %	15.000 - 17.000		
Iron	Fe %	3.000 max.	Mechanical Properties	
Phosphorus	P %	0.025 max.	Tensile Strength in Mpa	690 - 950
Sulphur	S %	0.015 max.	Yield Strength in Mpa	330 min.
Nickel	Ni %	Balance	Elongation in %	45 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	240 min.
-	-	-	Impact in Joule	120 @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.