



Material - DIN 2.4710

Standard Specification for Strips and Sheets of Nickel and Nickel Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4710 Strips and Sheets of Nickel and Nickel Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Strip and Sheet

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.100 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	6.000 - 10.000		
Cobalt	Co %	1.000 max.		
Aluminium	Al %	0.500 max.		
Copper	Cu %	0.500 max.		
Molybdenum	Mo %	21.000 - 25.000		
Iron	Fe %	5.000 - 8.000	Mechanical Properties	
Phosphorus	P %	0.020 max.	Tensile Strength in Mpa	720 min.
Sulphur	S %	0.015 max.	Yield Strength in Mpa	320 min.
Nickel	Ni %	Balance	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	240 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
NiMo23Cr8Fe	DIN	Germany	Strip and Sheet
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.