



Material - DIN 2.4889

Standard Specification for Strips and Sheets of Nickel and Nickel Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4889 Strips and Sheets of Nickel and Nickel Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Strip and Sheet

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.120	As-Cast or Annealing or Age Hardning	
Silicon	Si %	2.500 - 3.000		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	26.000 - 29.000		
Cobalt	Co %	1.500 max.		
Iron	Fe %	21.000 - 25.000		
Cerium	Ce %	0.030 - 0.090		
Copper	Cu %	0.300 max.		
Phosphorus	P %	0.020 max.		
Nickel	Ni %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 620 - 820 Yield Strength in Mpa 240 min. Elongation in % 35 min. Reduction of Area in % - Hardness in HB 220 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4889	GOST	Russia	Casting
NiCr28FeSiCe	GOST	Russia	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.