



Material - DIN EN 12164 CuNi10Zn42Pb2 (CW402J)

Standard Specification for Copper-Nickel-Zinc Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - DIN EN 12164 CuNi10Zn42Pb2 Copper-Nickel-Zinc Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.	As Raw or Solution Heat Treated	
Manganese	Mn %	0.500 max.		
Nickel	Ni %	9.000 - 11.000		
Lead	Pb %	1.000 - 2.500		
Tin	Sn %	0.200 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	45.000 - 48.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 510 min. Yield Strength in Mpa 350 min. Elongation in % 8 min. Reduction of Area in % - Hardness in HV 160 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi10Zn42Pb2	SFS	Finland	Rod
CW402J	SFS	Finland	Rod
CuNi10Zn42Pb2	EN	European Union	Rod
CW402J	EN	European Union	Rod
CuNi10Zn42Pb2	UNI	Italy	Rod
CW402J	UNI	Italy	Rod
CuNi10Zn42Pb2	CSN	Czech Republic	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.