



## Material - DIN EN 12844 ZP0810 I ZP8

**Standard Specification For Zinc and Zinc Alloy Castings** 

**Group - Non-Ferrous Zinc Alloys** 

Sub Group - DIN EN 12844 ZP0810 I ZP8 Zinc and Zinc Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Casting** 

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.000 - 8.800		
Copper	Cu %	0.800 - 1.300		
Magnesium	Mg %	0.015 - 0.030		
Lead	Pb %	0.006 max.	As-Cast	
Cadmium	Cd %	0.006 max.		
Tin	Sn %	0.003 max.		
Iron	Fe %	0.060 max.		
Nickel	Ni %	0.020 max.		•
Silicon	Si %	0.045 max.	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	370 min.
-	-	-	Yield Strength in Mpa	220 min.
-	-	-	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	100 min.
-	-	-	Impac <mark>t in Joule</mark>	40 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B 240 ZA8	ASTM	USA	Ingot and Casting	
-	-	·	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.