



Material - DIN EN 1706 AC-48100

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - DIN EN 1706 Aluminium and Aluminium Alloys - Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment															
Copper	Cu %	4.000 - 5.000	As-Cast															
Iron	Fe %	1.300 max.																
Magnesium	Mg %	0.250 - 0.650																
Manganese	Mn %	0.500 max.																
Nickel	Ni %	0.300 max.																
Silicon	Si %	16.000 - 18.000																
Tin	Sn %	0.150 max.																
Titanium	Ti %	0.250 max.																
Zinc	Zn %	1.500 max.																
Other	Ot%	0.250 max.																
Aluminium	Al %	Balance	<table border="1"> <thead> <tr> <th colspan="2">Mechanical Properties</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength in Mpa</td> <td>200 - 295</td> </tr> <tr> <td>Yield Strength in Mpa</td> <td>160 - 260</td> </tr> <tr> <td>Elongation in %</td> <td>1 min.</td> </tr> <tr> <td>Reduction of Area in %</td> <td>-</td> </tr> <tr> <td>Hardness in HB</td> <td>90 - 125</td> </tr> <tr> <td>Impact in Joule</td> <td>-</td> </tr> </tbody> </table>		Mechanical Properties		Tensile Strength in Mpa	200 - 295	Yield Strength in Mpa	160 - 260	Elongation in %	1 min.	Reduction of Area in %	-	Hardness in HB	90 - 125	Impact in Joule	-
Mechanical Properties																		
Tensile Strength in Mpa	200 - 295																	
Yield Strength in Mpa	160 - 260																	
Elongation in %	1 min.																	
Reduction of Area in %	-																	
Hardness in HB	90 - 125																	
Impact in Joule	-																	
-	-	-																
-	-	-																
-	-	-																
-	-	-																
-	-	-																

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 390	AA	USA	Casting
EN AC-48100	ASME	USA	Casting
EN AC-48100	UNI	Italy	Casting
EN AC-48100	AFNOR NF	France	Casting
EN AC-48100	UNE	Spain	Casting
EN AC-48100	SFS	Finland	Casting
EN AC-48100	MSZ	Hungary	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.