GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - DIN EN 1706 EN AC-46000 I EN AC-Al Si9Cu3(Fe)

Standard Specification for Aluminium and Aluminium Alloys - Castings

Group - Non-Ferrous Aluminium Alloys

Sub Group - DIN EN 1706 EN AC-46000 I EN AC-Al Si9Cu3(Fe) Aluminium and Aluminium Alloys - Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Silicon	Si %	8.000 - 11.000
Iron	Fe %	1.300 max.
Copper	Cu %	2.000 - 4.000
Manganese	Mn %	0.550 max.
Magnesium	Mg %	0.050 - 0.550
Chromium	Cr %	0.150 max.
Nickel	Ni %	0.550 max.
Zinc	Zn %	1.200 max.
Lead	Pb %	0.350 max.
Tin	Sn %	0.250 max.
Titanium	Ti %	0.250 max.
Other	Ot %	0.250 max.
Aluminium	Al %	Balance
-	-	-
-	-	-

Heat Treatment
As-Cast or Solution Aging

Mechanical Properties	
Tensile Strength in Mpa	-
Proof Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
AC-46000	UNS	USA	Casting
1706 EN AC-46000	EN	European Union	Casting
1706 EN AC-Al Si9Cu3(Fe)	EN	European Union	Casting
EN 1676 EN AB-46000	DIN	Germany	Casting
EN 1676 EN AB-Al Si9Cu3(Fe)	DIN	Germany	Casting
H 5202 AC8B	JIS	Japan	Casting
H 2211 AC8B.1	JIS	Japan	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.