



Material - DIN EN 1982 CB750S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - DIN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.100 max.	As-Cast	
Iron	Fe %	0.700 max.		
Manganese	Mn %	0.200 max.		
Nickel	Ni %	1.000 max.		
Phosphorus	P %	0.020 max.		
Lead	Pb %	1.000 - 2.800		
Silicon	Si %	0.040 max.		
Tin	Sn %	1.500 max.		
Cu + Ni	Cu%+Ni%	63.000 - 66.000	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	180 min.
-	-	-	Yield Strength in Mpa	70 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	45 - 50
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC750S	BS	British	Ingot and Casting
CB750S	EN	European Union	Ingot and Casting
CB750S	UNI	Italy	Ingot and Casting
CB750S	BS	British	Ingot and Casting
CAC202	JIS	Japan	Casting
CuZn33Pb2-B	PN	Poland	Ingot and Casting
CuZn33Pb2-B	AFNOR NF	France	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.