



## Material - DIN EN 1982 CB760S

**Standard Specification for Copper and Copper Alloys - Ingots and Castings**

**Group - Non-Ferrous Copper Alloy**

**Sub Group - DIN EN 1982 Copper and Copper Alloys - Ingots and Castings**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Ingot and Casting**

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Arsenic	As %	0.060 - 0.150		
Iron	Fe %	0.150 max.		
Manganese	Mn %	0.100 max.		
Nickel	Ni %	0.100 max.		
Lead	Pb %	0.500 max.		
Silicon	Si %	0.020 max.		
Tin	Sn %	0.300 max.		
Copper	Cu %	83.000 - 87.500		
Zinc	Zn %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	160 min.
-	-	-	Yield Strength in Mpa	70 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	45 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC760S	BS	British	Ingot and Casting
CB760S	ONORM	Australia	Ingot and Casting
CB760S	CSN	Czech Republic	Ingot and Casting
CB760S	AFNOR NF	France	Ingot and Casting
CuSn15As-B	ONORM	Australia	Ingot and Casting
CuSn15As-B	AFNOR NF	France	Ingot and Casting
CuSn15As-B	DIN	Germany	Ingot and Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.