



## Material - DIN EN 1982 CC755S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group - Non-Ferrous Copper Alloy** 

Sub Group - DIN EN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Ingot and Casting** 

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.400 - 0.700		
Iron	Fe %	0.050 - 0.200		
Manganese	Mn %	0.050 max.	As-Cast	
Nickel	Ni %	0.200 max.		
Lead	Pb %	1.200 - 1.700		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.300 max.		
Copper	Cu %	59.500 - 61.000		-
Zinc	Zn %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	310 - 350
-	-		Yield Strength in Mpa	180 - 210
-	-	-	Elongation in %	3 - 13
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	90 - 100
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CB755S	BS	British	Ingot and Casting	
CC755S	MSZ	Hungary	Ingot and Casting	
CC755S	UNI	Italy	Ingot and Casting	
CC755S	AFNOR NF	France	Ingot and Casting	
CuZn39Pb1AlB-C	UNE	Spain	Ingot and Casting	
CuZn39Pb1AlB-C	CSN	Czech Republic	Ingot and Casting	
CuZn39Pb1AlB-C	MSZ	Hungary	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.