

## Material - DIN G-Ni95

## Standard Specification for Nickel and Nickel-Copper Alloy Casting

**Group - Non-Ferrous Nickel Alloys** 

Sub Group - DIN G-Ni95 Nickel and Nickel-Copper Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	1.000 max.		
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.500 max.	As-Cast or Annealing or Age Hardning	
Copper	Cu %	1.200 max.		
Iron	Fe %	1.000 max.		
Other	Ot%	0.200 max.		
Ni + Co	Ni% + Co%	95.000 min.		
-	-			
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	320 min.
-	-	-	Yield Strength in Mpa	120 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	80 min.
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry		
2.417	DIN	Germany	Casting		
-	-	-	-		
-	-	-			
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## **ONE STOP SOLUTION FOR METAL PARTS**