



Material - DIN G-NiCu30Si3

Standard Specification for Nickel and Nickel-Copper Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4367 Nickel and Nickel-Copper Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.		
Silicon	Si %	2.700 - 3.700		
Magnesium	Mg %	0.120 max.		
Copper	Cu %	27.000 - 33.000	As-Cast or Annealing or Age Hardning	
Iron	Fe %	1.000 - 2.500		
Aluminium	Al %	0.500 - 1.500		
sulphur	S %	0.010 max.		
Lead	Pb %	0.010 max.		
Titanium	Ti %	0.200 max.	Mechanical Properties	
Other	Ot%	1.000 max.	Tensile Strength in Mpa	650 min.
Ni + Co	Ni% + Co%	61.000 - 68.000	Yield Strength in Mpa	350 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
	-	-	Hardness in HB	220 min.
-	-	-	Impact in Joule	-
-		-		-

Cross Reference Table					
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry		
2.4367	DIN	Germany	Casting		
-	_	-	-		
-	-	-			
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS