



## Material - DIN NiCr16 Fe 7 TiAl

### Standard Specification for Nickel and Nickel Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN NiCr16 Fe 7 TiAl Nickel and Nickel Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.000 - 17.000		
Copper	Cu %	0.500 max.		
Aluminium	Al %	0.800 - 1.600		
Iron	Fe %	5.000 - 9.000		
Niobium	Nb %	0.700 - 1.200		
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.010 max.		
Titanium	Ti %	2.000 - 2.600	Mechanical Properties	
Nickel	Ni %	70.000 min.	Tensile Strength in Mpa	782 min.
-	-	-	Yield Strength in Mpa	391 min.
-	-	-	Elongation in %	42 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4694	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.