



Material - DIN NiCr20AlSi

Standard Specification for Nickel and Chromium Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN NiCr20AlSi Nickel and Chromium Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.500 min.		
Silicon	Si %	1.000 min.	As-Cast or Annealing or Age Hardning	
Manganese	Mn %	0.500 min.		
Chromium	Cr %	20.000 min.		or Age Hardning
Iron	Fe %	0.500 min.		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		-
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	1000 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
2.4872	DIN	Germany	Casting	
-	-	·	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.