

Material - DIN NiCr20Co13Mo4Ti3Al

Standard Specification for Nickel and Nickel Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN NiCr20Co13Mo4Ti3Al Nickel and Nickel Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 - 0.100		
Silicon	Si %	0.150 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	18.000 - 21.000	As-Cast or Annealing or Age Hardning	
Aluminium	Al %	1.200 - 1.600		
Boron	В%	0.003 - 0.010		
Cobalt	Co %	12.000 - 15.000		
Copper	Cu %	0.100 max.		
Iron	Fe %	2.000 max.	Mechanical Properties	
Molybdenum	Mo %	3.500 - 5.000	Tensile Strength in Mpa	1100 min.
Phosphorus	P %	0.015 max.	Yield Strength in Mpa	760 min.
Sulphur	S %	0.015 max.	Elongation in %	15 min.
Titanium	Ti %	2.800 - 3.300	Reduction of Area in %	18 min.
Zirconium	Zr %	0.020 - 0.080	Hardn <mark>ess in H</mark> V	320 - 410
Nickel	Ni %	Balance	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
2.4654	DIN	International	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS