



Material - DIN NiCr21Mo14W

Standard Specification for Nickel, Molybdenum and Chromium Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN NiCr21Mo14W Nickel, Molybdenum and Chromium Alloy Casting Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.		
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	20.000 - 22.500		
Cobalt	Co %	2.500 max.		
Molybdenum	Mo %	12.500 - 14.500		
Iron	Fe %	2.000 - 6.000		
Phosphorus	P %	0.025 max.		•
Sulphur	S %	0.015 max.	Mechanical Properties	
Vanadium	V %	0.350 max.	Tensile Strength in Mpa	690 min.
Tungsten	W %	2.500 - 3.500	Yield Strength in Mpa	310 min.
Nickel	Ni %	Balance	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	240 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
2.4602	DIN	Germany	Casting	
-	-	·	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.