



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - DIN NiMo16Cr15W

Standard Specification for Nickel and Nickel Alloy Casting

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN NiMo16Cr15W Nickel and Nickel Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.500 - 16.500		
Cobalt	Co %	2.500 max.		
Iron	Fe %	4.000 - 7.000		
Molybdenum	Mo %	15.000 - 17.000		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.010 max.		
Vanadium	V %	0.350 max.		
Tungsten	W %	3.000 - 4.500	Mechanical Properties	
Nickel	Ni %	Balance	Tensile Strength in Mpa	690 min.
-	-	-	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	240 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4819	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS