



Material - DIN SG-NiMo16Cr16Ti

Standard Specification for Nickel and Nickel Alloy Rod, Wire and Strips

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN SG-NiMo16Cr16Ti Nickel and Nickel Alloy Rod, Wire and Strips

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod, Wire and Strips

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.000 - 18.000		
Iron	Fe %	3.000 max.		
Molybdenum	Mo %	14.000 - 17.000		
sulphur	S %	0.015 max.		
Titanium	Ti %	0.200 - 0.700		
Other	Ot%	0.500 max.		
Ni + Co	Ni% + Co%	56.000 min.		
-	-	-	Mechanical Properties Tensile Strength in Mpa 650 min. Yield Strength in Mpa 300 min. Elongation in % 25 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 60 @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4611	DIN	Germany	Rod, Wire and Strips
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.