

Material - DIN X 1 NiCrSi 24-9-7

Standard Specification for Chromium, Chromium-Nickel and Silicon Alloy Steel Plate, Sheet and Strip for Corrosion and Heat Resisting Service

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN X 1 NiCrSi 24-9-7 Chromium, Chromium-Nickel and Silicon Alloy Steel Plate, Sheet and Strip for Corrosion and Heat Resisting Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.		
Silicon	Si %	6.500 - 8.000		
Manganese	Mn %	2.000 max.	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	8.000 - 11.000		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	0.500 max.		
Phosphorus	P %	0.025 max.		
Nickel	Ni %	22.000 - 25.000		•
Aluminium	Al %	0.500 max.	Mechanical P	roperties
Iron	Fe %	Balance	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A 946 Grade S70003	ASTM	USA	Plate, Sheet and Strip	
A 953 S70003	ASTM	USA	Tube	
A 954 S70003	ASTM	USA	Pipe	
A 968 S70003	ASTM	USA	Bars and Shapes	
1.439	DIN	Germany	Plate, Sheet and Strip	
S70003	UNS	USA	Plate, Sheet and Strip	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.