



Material - EN 1706 AC-48100

Standard Specification for Aluminium Alloy Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - EN 1706 Aluminium Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	4.000 - 5.000	As-Cast	
Iron	Fe %	1.300 max.		
Magnesium	Mg %	0.250 - 0.650		
Manganese	Mn %	0.500 max.		
Silicon	Si %	16.000 - 18.000		
Tin	Sn %	0.150 max.		
Titanium	Ti %	0.250 max.		
Zinc	Zn %	1.500 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 200 - 295 Yield Strength in Mpa 160 - 260 Elongation in % 1 min. Reduction of Area in % - Hardness in HB 90 - 125 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM30	BS	British	Ingot and Casting
390.0	AA	USA	Casting
ADC 14	JIS	Japan	Casting
EN AC-48100	DIN	Germany	Casting
AlSi17Cu4Mg	ISO	International	Casting
ALDC 14	JIS	Japan	Casting
EN AC-48100	UNE	Spain	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.