



Material - EN CuZn38Pb4

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group - Non Ferrous Copper Alloys

Sub Group - EN CuZn38Pb4 Copper and Copper Alloy Rod for Free Machining Purpose

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.050 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.300 max.		
Nickel	Ni %	0.300 max.		
Lead	Pb %	3.500 - 4.200		
Tin	Sn %	0.300 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	57.000 - 59.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	360 min.
-	-	-	Yield Strength in Mpa	150 - 520
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	90 - 160
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn38Pb4	DIN	Germany	Rod
C 3604 W	JIS	Japan	Rod
C 3605 BD	JIS	Japan	Rod
C 3605 BE	JIS	Japan	Rod
CW609N	EN	European Union	Rod
CuZn38Pb4	AFNOR NF	France	Rod
CW609N	AFNOR NF	France	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.