

Material - Gravity Incoloy A-286

Standard Specification for Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - Standard Specification for Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	13.500 - 16.000	As-Cast or Annealing or Age Hardning	or Age Hardning
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	1.000 - 1.500		
Aluminium	Al %	0.350 max.		
Boron	B %	0.003 - 0.010		
Titanium	Ti %	1.900 - 2.300	Mechanical Properties	
Vanadium	V %	0.100 - 0.500	Tensile Strength in Mpa	600 - 1500
Nickel	Ni %	24.000 - 27.000	Yield Strength in Mpa	737.4 min.
Iron	Fe %	Balance	Elongation in %	29.300 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	31 max.
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A 959 Type 660	ASTM	USA	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire		
F 2281 660	ASTM	USA	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire		
-	-		-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.