

Material - Gravity Incoloy Alloy 28

Standard Specification for Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - Gravity Incoloy Alloy 28 Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.500 max.		
Chromium	Cr %	26.000 - 28.000	As-Cast or Annealing or Age Hardning	
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	3.000 - 4.000		
Copper	Cu %	0.600 - 1.400		
Phosphorus	P %	0.030 max.		
Nickel	Ni %	30.000 - 34.000	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	500 - 896
-	-	-	Yield Strength in Mpa	214 - 758
-	-	-	Elongation in %	15 - 40
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	33 - 90
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A 213 N08028	ASTM	USA	Tube	
A 988 N08028	ASTM	USA	Flanges, Fittings, Valves and Parts	
A312 N08028	ASTM	USA	Pipe	
SA-213 N08028	ASME	USA	Tube	
SA-312 N08028	ASME	USA	Pipe	
SA-988 N08028	ASME	USA	Flanges, Fittings, Valves and Parts	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.