

## Material - Gravity Incoloy Alloy 890

Standard Specification for Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

**Group - Non-Ferrous Nickel Alloys** 

Sub Group - Gravity Incoloy Alloy 890 Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.		
Silicon	Si %	1.800 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	25.000 max.	As-Cast or Annealing or Age Hardning	
Sulphur	S %	0.015 max.		
Phosphorus	P %	0.030 max.		
Molybdenum	Mo %	1.500 max.		
Copper	Cu %	0.750 max.		
Aluminium	Al %	0.100 max.	Mechanical Properties	
Niobium	Nb %	0.400 max.	Tensile Strength in Mpa	652 min.
Tantalum	Ta %	0.200 max.	Yield Strength in Mpa	272 - 334
Titanium	Ti %	1.000 max.	Elongation in %	46.5 - 46.6
Nickel	Ni %	42.000 max.	Reduction of Area in %	60.1 - 62.7
Iron	Fe %	Balance	Hardness in HRC	14 - 33
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
-	-	·	-		
-	-	ì	-		
-	-		-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.