

Material - Gravity Incoloy Alloy 945

Standard Specification for Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - Gravity Incoloy Alloy 945 Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------|-----------|
| Carbon | C % | 0.005 - 0.040 | | |
| Silicon | Si % | 0.500 max. | | |
| Manganese | Mn % | 1.000 max. | As-Cast or Annealing or Age Hardning | |
| Chromium | Cr % | 19.500 - 23.000 | | |
| Sulphur | S % | 0.010 max. | | |
| Molybdenum | Mo % | 3.000 - 4.000 | | |
| Copper | Cu % | 1.500 - 3.000 | | |
| Aluminium | Al % | 0.010 - 0.700 | | |
| Phosphorus | P % | 0.020 max. | Mechanical Properties | |
| Niobium | Nb % | 2.800 - 3.500 | Tensile Strength in Mpa | 1034 min. |
| Titanium | Ti % | 0.500 - 2.500 | Yield Strength in Mpa | 862 min. |
| Nickel | Ni % | 46.500 - 48.000 | Elongation in % | 15 min. |
| Iron | Fe % | Balance | Reduction of Area in % | 20 min. |
| - | - | - | Hardness in HRC | 34 - 46 |
| - | - | - | Impact in Joule | 54 @RT |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|---|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| N09945 | UNS | USA | Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire | | |
| - | - | | - | | |
| - | - | | - | | |
| - | - | - | - | | |
| - | - | - | - | | |
| - | - | - | - | | |
| - | - | - | - | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.