



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - Gravity Inconel 693

### Standard Specification for Nickel and Nickel-Related Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - Gravity Inconel 693 Nickel and Nickel-Related Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Sheet

Chemical Composition			Heat Treatment	
Carbon	C %	0.002 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.200 max.		
Manganese	Mn %	0.200 max.		
Chromium	Cr %	29.000 max.		
Aluminium	Al %	3.000 max.		
Niobium	Nb %	0.600 max.		
Titanium	Ti %	0.400 max.		
Iron	Fe %	3.500 max.		
Nickel	Ni %	60.500 max.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	690 min.
-	-	-	Yield Strength in Mpa	345 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N06693	UNS	USA	Sheet
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**