

Material - Gravity NILO Alloy 48

Standard Specification for Nickel-Iron Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - Gravity NILO Alloy 48 Nickel-Iron Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Nickel	Ni %	48.000 min.		
Iron	Fe %	52.000 max.		
-	-	-		
-	-	-	As-Cast or Annealing or Age Hardning	
-	-			
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	520 min.
-	-	-	Yield Strength in Mpa	260 min.
-	-	-	Elongation in %	43 min.
-	-	-	Reduction of Area in %	72 min.
-	-	-	Hardness in HRC	80 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
Dilaton 48	Gravity	India	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire		
-	-		-		
-	-		-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.