



Material - Gravity R-Ni 99,2

Standard Specification for Nickel and Nickel Alloys Strips and Sheets

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4066 Nickel and Nickel Alloys Strips and Sheets

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Strip and Sheet

Chemical Composition			Heat Treatment			
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning			
Silicon	Si %	0.250 max.				
Manganese	Mn %	0.350 max.				
Copper	Cu %	0.250 max.				
Iron	Fe %	0.400 max.				
Magnesium	Mg %	0.150 max.				
Sulphur	S %	0.005 max.				
Titanium	Ti %	0.100 max.				
Ni + Co	Ni% + Co%	99.200 min.				
-	-	-				
-	-	-	<th colspan="2">Mechanical Properties</th>		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.		
-	-	-	Yield Strength in Mpa	-		
-	-	-	Elongation in %	2 min.		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in HRC	200 max.		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4066	DIN	Germany	Strip and Sheet
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.