

## Material - Gravity Udimet Alloy 188

Standard Specification for Nickel-Iron Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

**Group - Non-Ferrous Cobalt Alloys** 

Sub Group - Gravity Udimet Alloy 188 Nickel-Iron Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150		
Silicon	Si %	0.200 - 0.500		
Manganese	Mn %	1.250 max.	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	20.000 - 24.000		
Boron	В%	0.015 max.		
Iron	Fe %	3.000 max.		
Lanthanum	La %	0.020 - 0.120		
Tungsten	W %	13.000 - 16.000		-
Nickel	Ni %	20.000 - 24.000	Mechanical Properties	
Cobalt	Co %	Balance	Tensile Strength in Mpa	963 - 1597.2
-	-	-	Yield Strength in Mpa	446 - 1450.1
-	-	-	Elongation in %	6.454 - 55
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
HS-188	SAE	USA	Sheet, Strip and Plate		
R30188	UNS	USA	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire		
-	-		-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.