



## Material - IS 10773 Grade 1

## Standard Specification for Wrought Copper Tubes for Refrigeration and Air-Conditioning Purposes

**Group - Non-Ferrous Copper Alloy** 

Sub Group - IS 10773 Wrought Copper Tubes for Refrigeration and Air-Conditioning Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Phosphorus	Р%	0.004 - 0.015		
Copper	Cu %	99.900 min.		
-	-	-		
-	-	-	As Drawn or Annealing	nealing
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	/-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	205 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Cu DLP-HB	IS	India	Tube	
Cu DLP-HD	IS	India	Tube	
Cu DLP-O	IS	India	Tube	
C 1201 CB	JIS	Japan	Billet and Cake	
C 1201 CC	JIS	Japan	Billet and Cake	
C 1201	KS	Korea	Rod and Bar	
C 1201 CB	KS	Korea	Billet and Cake	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.