



Material - IS 10773 Grade 2

Standard Specification for Wrought Copper Tubes for Refrigeration and Air-Conditioning Purposes

Group - Non-Ferrous Copper Alloy

Sub Group - IS 10773 Wrought Copper Tubes for Refrigeration and Air-Conditioning Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Lead	Pb %	0.010 max.	As Drawn or Annealing	
Tin	Sn %	0.010 max.		
Iron	Fe %	0.030 max.		
Arsenic	As %	0.050 max.		
Nickel	Ni %	0.100 max.		
Phosphorus	P %	0.015 - 0.040		
Other	Ot%	0.060 max.		
Copper	Cu %	99.850 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	205 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuDHP-HB	IS	India	Plate, Sheet, Strip and Foil
CuDHP-HD	IS	India	Plate, Sheet, Strip and Foil
CuDHP-O	IS	India	Plate, Sheet, Strip and Foil
Cu DHP	IS	India	Tube
CuDHP-HA	IS	India	Plate, Sheet, Strip and Foil
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.