



Material - IS 12443 Brass CuZn28As

Standard Specification for Rolled Brass Plates for General Engineering

Group - Non-Ferrous Copper Alloy

Sub Group - IS 12443 Rolled Brass Plates for General Engineering

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate

Chemical	Composition	า	Heat Treatment
Lead	Pb %	0.075 max.	
Iron	Fe %	0.060 max.	
Arsenic	As %	0.020 - 0.060	
Other	Ot%	0.300 max.	As Raw or Annealing or Strain Hardening
Copper	Cu %	70.000 - 73.000	
Zinc	Zn %	Balance	
-	-	-	
-	-	-	
-	-	-	Mechanical Properties
-	-		Tensile Strength in Mpa 280 min.
-	-	-	Yield Strength in Mpa -
-	-	-	Elongation in % 40 min.
-	-	-	Reduction of Area in % -
-	-	-	Hardness in BHN -
-	-	-	Impac <mark>t in Joule</mark>

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CZ105	BS	British	Plate	
-	-	•	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.