



Material - IS 14811 CuATP-HB

Standard Specification for Rolled Copper Plate, Sheet, Strip and Foils for General Engineering Purposes

Group - Non-Ferrous Copper Alloy

Sub Group - IS 14811 Rolled Copper Plate, Sheet, Strip and Foils for General Engineering Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plate, Sheet, Strip and Foils

Chemical Composition			Heat Treatment	
Arsenic	As %	0.200 - 0.500		
Bismuth	Bi %	0.005 max.	As Drawn or Annealing or Half Hardening or Temperin & Annealing or Annealing	
Iron	Fe %	0.020 max.		Jardaning or Tomporing
Nickel	Ni %	0.150 max.		
Oxygen	0 %	0.100 max.		anneanng
Lead	Pb %	0.020 max.		
Antimony	Sb %	0.010 max.		
Se + Te	Se% + Te%	0.030 max.		
Tin	Sn %	0.030 max.	Mechanical Properties	
Cu + Ag	Cu% + Ag%	99.200 min.	Tensile Strength in Mpa	250 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	75 - 90
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Cu-ATP	IS	India	Ingot and Casting	
CuATP-HA	IS	India	Plate, Sheet, Strip and Foils	
CuATP-HD	IS	India	Plate, Sheet, Strip and Foils	
CuATP-O	IS	India	Plate, Sheet, Strip and Foils	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.