



Material - IS 14811 CuFRTP-1-HA

Standard Specification for Rolled Copper Plate, Sheet, Strip and Foils for General Engineering Purposes

Group - Non-Ferrous Copper Alloy

Sub Group - IS 14811 Rolled Copper Plate, Sheet, Strip and Foils for General Engineering Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plate, Sheet, Strip and Foils

Chemical Composition			Heat Treatment	
Arsenic	As %	0.020 max.		
Bismuth	Bi %	0.003 max.		
Iron	Fe %	0.010 max.	As-Cast	
Nickel	Ni %	0.050 max.		
Oxygen	0 %	0.100 max.		
Other	Ot%	0.050 max.		
Lead	Pb %	0.005 max.		
Antimony	Sb %	0.005 max.		
Se + Te	Se% + Te%	0.025 max.	Mechanical Properties	
Tin	Sn %	0.010 max.	Tensile Strength in Mpa	250 min.
Cu + Ag	Cu% + Ag%	99.850 min.	Yield Strength in Mpa	-
-	-	-	Elongation in %	15 min.
	-		Reduction of Area in %	-
-	-	-	Hardness in HV	75 - 90
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Cu-FRTP-1	IS	India	Ingot and Casting	
CuFRTP-1-HB	IS	India	Plate, Sheet, Strip and Foils	
CuFRTP-1-HD	IS	India	Plate, Sheet, Strip and Foils	
CuFRTP-1-O	IS	India	Plate, Sheet, Strip and Foils	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.