



Material - IS 14811 CuFRTP-2-O

Standard Specification for Rolled Copper Plate, Sheet, Strip and Foils for General Engineering Purposes

Group - Non-Ferrous Copper Alloy

Sub Group - IS 14811 Rolled Copper Plate, Sheet, Strip and Foils for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Sheet, Strip and Foils

| Chemical Composition | | | Heat Treatment | |
|----------------------|-----------|-------------|---|--|
| Arsenic | As % | 0.100 max. | As-Cast | |
| Bismuth | Bi % | 0.020 max. | | |
| Iron | Fe % | 0.030 max. | | |
| Nickel | Ni % | 0.050 max. | | |
| Oxygen | O % | 0.100 max. | | |
| Lead | Pb % | 0.100 max. | | |
| Antimony | Sb % | 0.050 max. | | |
| Se + Te | Se% + Te% | 0.007 max. | | |
| Tin | Sn % | 0.050 max. | | |
| Cu + Ag | Cu% + Ag% | 99.500 min. | | |
| - | - | - | Mechanical Properties Tensile Strength in Mpa 195 min. Yield Strength in Mpa - Elongation in % 35 min. Reduction of Area in % - Hardness in HV 55 min. Impact in Joule - | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|---------|-------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| Cu-FRTP-2 | IS | India | Ingot and Casting |
| CuFRTP-2-HA | IS | India | Plate, Sheet, Strip and Foils |
| CuFRTP-2-HB | IS | India | Plate, Sheet, Strip and Foils |
| CuFRTP-2-HD | IS | India | Plate, Sheet, Strip and Foils |
| - | - | - | - |
| - | - | - | - |
| - | - | - | - |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.