



## Material - IS 1545 CuNi30Mn1Fe

### Standard Specification for Solid Drawn Copper and Copper Alloy Tube for Condenser and Heat Exchangers

Group - Non-Ferrous Copper Alloy

Sub Group - IS 1545 Solid Drawn Copper and Copper Alloy Tube for Condenser and Heat Exchangers

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Lead	Pb %	0.050 max.	As Drawn or Annealing or Half Hardening or Tempering & Annealing or Annealing	
Iron	Fe %	0.400 - 1.000		
Manganese	Mn %	0.500 - 1.000		
Nickel	Ni %	29.000 - 33.000		
Zinc	Zn %	0.500 max.		
Other	Ot%	0.300 max.		
Copper	Cu %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa   360 min. Yield Strength in Mpa   - Elongation in %   35 min. Reduction of Area in %   - Hardness in HV 5   115 max. Impact in Joule   -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi30Mn1Fe-HD	IS	India	Tube
CuNi30Mn1Fe-O	IS	India	Tube
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.