



## Material - IS 1545 CuZn29Sn1As-TA

Standard Specification for Solid drawn Copper and Copper Alloy Tubes for Condenser and Heat Exchangers

**Group - Non-Ferrous Copper Alloy** 

Sub Group - IS 1545 Solid drawn Copper and Copper Alloy Tubes for Condenser and Heat Exchangers Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Arsenic	As %	0.020 - 0.060		
Iron	Fe %	0.060 max.	As Drawn or Annealing or Half Hardening or Temperin & Annealing or Annealing	
Nickel	Ni %	0.100 max.		Hardoning or Tomporing
Other	Ot%	0.300 max.		, ,
Lead	Pb %	0.070 max.		
Tin	Sn %	0.900 - 1.500		
Copper	Cu %	70.000 - 73.000		
Zinc	Zn %	Balance		
-	-		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	340 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	55 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HV</mark>	80 - 150
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CuZn29Sn1As	IS	India	Tube	
CuZn29Sn1As-HD	IS	India	Tube	
CuZn29Sn1As-O	IS	India	Tube	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.