



Material - IS 191 Cu-ETP

Standard Specification for Copper

Group - Non-Ferrous Copper Alloy

Sub Group - IS 191 Copper

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Lead	Pb %	0.005 max.	As-Cast	
Oxygen	O %	0.045 max.		
Cu + Ag	Cu% + Ag%	99.90 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Cu FRHC	IS	India	Ingot and Casting
CuCATH-HB	IS	India	Strip
CuCATH-HD	IS	India	Strip
CuCATH-O	IS	India	Strip
CuETP-HA	IS	India	Plate, Sheet, Strip and Foils
CuETP-HB	IS	India	Strip
C 101	BS	British	Rod and Section

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.