



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - IS 2378 Cu Zn 39

**Standard Specification for Code for Designation of Copper and Copper Alloys**

**Group - Non-Ferrous Copper Alloy**

**Sub Group - IS 2378 Code for Designation of Copper and Copper Alloys**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Casting, Rod and Bar**

Chemical Composition			Heat Treatment	
Lead	Pb %	0.300 max.	Annealing or Half Hardening or Hardening	
Tin	Sn %	0.100 max.		
Iron	Fe %	0.150 max.		
Other	Other %	0.750 max.		
Copper	Cu %	58.500 - 61.500		
Zinc	Zn %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**