



## Material - IS 2378 G Cu Sn Pb 7 Zn 5 Pb2

**Standard Specification for Code for Designation of Copper and Copper Alloys**

**Group - Non-Ferrous Copper Alloy**

**Sub Group - IS 2378 Code for Designation of Copper and Copper Alloys**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Casting, Rod and Bar**

Chemical Composition			Heat Treatment	
Tin	Sn %	6.000 - 8.000	As-Cast	
Zinc	Zn %	4.000 - 6.000		
Lead	Pb %	1.000 - 3.000		
Antimony	Sb %	0.300 max.		
Iron	Fe %	0.350 max.		
Other	Ot%	0.500 max.		
Cu + Ni	Cu%+Ni%	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.