

## Material - IS 2704 CuZn35

## Standard Specification for Brass Wires for Cold-Headed and Machined Parts

**Group - Non-Ferrous Copper Alloy** 

Sub Group - IS 2704 Brass Wires for Cold-Headed and Machined Parts

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire

Chemical Composition			Heat Treatment	
Lead	Pb %	0.020 max.		
Iron	Fe %	0.050 max.		
Other	Ot%	0.300 max.		
Copper	Cu %	63.000 - 68.000	Tempering or Quarter Hardening or Half Hardening	ning or Half Hardening
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	345 - 410
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in H</mark> V	110 - 130
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS