



Material - IS 3167

Standard Specification for Solid Drawn Copper Tubes for General Engineering Purpose

Group - Non-Ferrous Copper Alloy

Sub Group - IS 3167 Solid Drawn Copper Tubes for General Engineering Purpose

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.010 max.	Cold Rolled & Annealing	
Arsenic	As %	0.020 max.		
Antimony	Sb %	0.010 max.		
Bismuth	Bi %	0.002 max.		
Manganese	Mn %	0.040 max.		
Iron	Fe %	0.050 max.		
Lead	Pb %	0.020 max.		
Tin	Sn %	0.010 max.		
Nickel	Ni %	0.100 max.		
Other	Ot%	0.005 max.		
Copper	Cu %	95.000 - 98.000	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.